



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 153 649 A1**

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
14.11.2001 Bulletin 2001/46

(51) Int Cl.⁷: **B01D 53/94, B01J 21/06,
B01J 23/02, B01J 23/58**

(21) Application number: **01304065.4**

(22) Date of filing: **04.05.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **11.05.2000 JP 2000138822**

(71) Applicant: **NGK INSULATORS, LTD.**
Nagoya-City, Aichi Prefecture 467-8530 (JP)

(72) Inventors:
• **Noda, Naomi**
Nagoya City, Aichi-prefecture 467-8530 (JP)
• **Suzuki, Junichi**
Nagoya City, Aichi-prefecture 467-8530 (JP)

(74) Representative: **Paget, Hugh Charles Edward et al**
MEWBURN ELLIS
York House
23 Kingsway
London WC2B 6HP (GB)

(54) **Catalyst for purification of exhaust gas**

(57) A catalyst for purification of exhaust gas includes a carrier, and a catalyst layer containing an alkali metal and/or an alkaline earth metal as an NO_x-adsorbing component, the catalyst layer being loaded on the carrier, in which catalyst the carrier-composing material

contains Si in an amount of 0.5 to 10.0% by weight as expressed as an oxide. Since the inclusion of Si can suppress the deterioration of the carrier caused by the alkali metal and/or the alkaline earth metal during the use of the catalyst, the catalyst can be used over a long period.

EP 1 153 649 A1

Description

Background of the Invention

(1) Field of the Invention

[0001] The present invention relates to a catalyst for purification of exhaust gas, containing an alkali metal and/or an alkaline earth metal as an NO_x-adsorbing component, particularly a catalyst for purification of an exhaust gas emitted from an internal combustion engine of gasoline vehicle, diesel vehicle or the like.

(2) Description of Related Art

[0002] In recent years, regulation for exhaust gas has become stricter, and lean burn engines, direct injection engines, etc. have come into wide use. In this connection, NO_x-adsorbing catalysts capable of effectively purifying the NO_x present in an exhaust gas, in a lean atmosphere have been put into practical use. As the NO_x-adsorbing component used in the NO_x-adsorbing catalyst, there are known alkali metals such as K, Na, Li, Cs and the like; alkaline earth metals such as Ba, Ca and the like; and rare earth elements such as La, Y and the like. Recently, it has been attempted to use, in particular, K which is superior in NO_x adsorption at high temperatures.

[0003] NO_x-adsorbing catalysts are generally constituted by loading a catalyst layer containing the above-mentioned NO_x-adsorbing component, on a carrier composed of an oxide type ceramic (e.g. cordierite) or a metallic material (e.g. Fe-Cr-Al alloy). Such a carrier, however, has a problem; that is, it is easily corroded and deteriorated by alkali metals or part of alkaline earth metals, particularly, Li, Na, K and Ca when they become active under the high temperatures of exhaust gas.

Summary of the Invention

[0004] In view of the above problem of the prior art, the present invention aims at providing a catalyst for purification of exhaust gas, obtained by loading, on a carrier, a catalyst layer containing an alkali metal and/or an alkaline earth metal as an NO_x-adsorbing component, which catalyst can suppress the deterioration of the carrier caused by the alkali metal and/or the alkaline earth metal and therefore can be used over a long period of time.

[0005] According to the present invention, there is provided a catalyst for purification of exhaust gas comprising: a carrier, and a catalyst layer containing an alkali metal and/or an alkaline earth metal, the catalyst layer being loaded on the carrier, in which catalyst the carrier-composing material contains Si in an amount of 0.5 to 10.0% by weight as expressed as an oxide.

Description of Preferred Embodiments

[0006] In the catalyst of the present invention, an alkali metal and/or an alkaline earth metal is used as the NO_x-adsorbing component, and a catalyst layer containing the component is loaded on a carrier composed of a material containing a given amount of Si. It is known that Si has high reactivity with alkali metals and alkaline earth metals and can easily form a compound oxide therewith. Hence, in the present invention, a small amount of Si (Si is reactive with alkali metals and alkaline earth metals as mentioned above) is allowed to be present in the material composing the carrier, or a carrier-composing material inherently containing a small amount of Si is used, whereby the alkali metal and/or the alkaline earth metal (which is an NO_x-adsorbing component and deteriorates the carrier) is allowed to react preferentially with the Si. As a result, the reaction of the alkali metal and/or the alkaline earth metal with the carrier-composing major component (other than Si) is suppressed and the deterioration of the carrier is suppressed.

[0007] In general, carrier-composing materials decrease their strengths when they are exposed to high temperatures together with an alkali metal-containing catalyst layer. However, when they contain a small amount of Si therein, their initial strength can be increased and, as a result, they can possess a strength necessary for catalyst carrier even if their strength is slightly decreased, for example, when they are exposed to high temperatures with an alkali-containing catalyst layer. Such an effect brought about by the inclusion of Si is striking in catalyst-composing ceramic materials, particularly in ceramic materials wherein the particles of the major component contain no Si therein and the bonding between the particles is relatively weak, such as alumina, aluminum titanate and the like. It is because Si bond the particles at the boundaries or assists such bonding.

[0008] In the present invention, the content of Si in the carrier-composing material is specifically 0.5 to 10.0% by weight, preferably 1.0 to 6.0% by weight, more preferably 2.0 to 5.0% by weight as expressed as an oxide content. When the content is less than 0.5% by weight, the effect by Si of protecting the catalyst-composing major component from the deterioration by alkali metal or alkaline earth metal is insufficient. A Si content of more than 10.0% by weight is not preferred because when there is used, as an alkali metal, K which is superior in NO_x-adsorption at high temperatures and which has recently drawn attention as an NO_x-adsorbing component, the reaction product between this K and Si increases the thermal expansion coefficient of the total carrier. When the content is less than 1.0% by weight, if the carrier is highly porous, the alkali metal or the alkaline earth metal diffuses easily into the inside of the carrier and the effect by Si of protecting the carrier-composing major component may be less. A content of more than 6.0%

by weight is not preferred because when K is used as an NO_x-adsorbing component, the reaction product between this K and Si decreases the softening point of the total carrier.

[0009] For the above-mentioned increase in initial strength, a Si content of 0.7% by weight or more as expressed as an oxide is effective. A Si content of 1.5% by weight or more is more preferred because a sufficient effect can be obtained. At a Si content of more than 8% by weight, however, the effect of initial strength increase levels off.

[0010] Si contained in the carrier-composing material can play a role even when present inside the particles of the carrier-composing major component or inside the particles of the carrier-composing minor component. However, in order for Si to effectively protect the particles of the carrier-composing major component from the deterioration, Si is preferably present at the particle boundaries or on the particles of the carrier-composing major component. As a matter of course, Si may be present in a mixed form of the above presences. When the carrier-composing material is aluminum titanate, the material may preferably contain further Mg and/or Fe in order to suppress the thermal decomposition at high temperatures and increase the strength.

[0011] In the catalyst of the present invention, when it is used for purification of exhaust gas from automobile (in this case, the catalyst is inevitably exposed to high temperatures), the carrier is allowed to have a thermal expansion coefficient of preferably $6.0 \times 10^{-6}/^{\circ}\text{C}$ or less, more preferably $2.0 \times 10^{-6}/^{\circ}\text{C}$ or less, further preferably $1.0 \times 10^{-6}/^{\circ}\text{C}$ or less in view of the thermal shock resistance, etc. When K is used as an NO_x-adsorbing component, the carrier is allowed, by the control of Si content therein, to have a thermal expansion coefficient of preferably $6.0 \times 10^{-6}/^{\circ}\text{C}$ or less, more preferably $4.0 \times 10^{-6}/^{\circ}\text{C}$ or less even after a K-containing catalyst layer has been loaded on the carrier and the resulting material has been heat-treated at 850°C for 50 hours.

[0012] In the present invention, the carrier has a porosity of preferably 5 to 50%, more preferably 10 to 40%, further preferably 10 to 25%. When the porosity of the carrier is less than 5%, the carrier may have a problem in coatability of catalyst layer thereon. When the porosity is more than 50%, the carrier may have insufficient strength. A porosity of 25% or less is preferred because it suppresses the diffusion of alkali metal or alkaline earth metal into carrier.

[0013] The present invention is effective when applied to various carrier-composing materials. Therefore, there is no particular restriction as to the kind of the carrier-composing material used, and ceramic, metallic and other materials can be used. The present invention is suitably applied to, for example, alumina, zirconia, titania, spinel (these are ceramics), zirconia type oxide typified by zirconyl phosphate, alumina type oxide typified by aluminum titanate, and titania type oxide. Of these, zirconyl phosphate, aluminum titanate, etc. all having a

low thermal expansion coefficient are particularly preferred. Incidentally, Si may be inherently present in the catalyst-composing material, or may be added to pure crystals containing no Si.

5 [0014] The carrier has no particular restriction as to the shape. Therefore, the above-mentioned effect of deterioration suppression is obtained when the carrier takes any of a cell structure (e.g. a monolithic honeycomb or a ceramic foam), pellets, beads, ring, etc. The effect is largest when the carrier is a honeycomb carrier constituted by a large number of through-holes (cells) surrounded by thin partition walls. The sectional shape, i.e. cell shape of each through-hole of this honeycomb carrier may be any of a circle, a polygon, a corrugation, etc. In recent years, NO_x-adsorbing catalysts have become to adopt a hexagonal cell in addition to conventional triangular and tetragonal cells, for uniform coating of catalyst layer. Therefore, application of the present invention to these honeycomb carriers is one preferred embodiment of the present invention. The shape of the honeycomb carrier may also be formed so as to fit the interior shape of the exhaust gas system in which the present catalyst is disposed.

15 [0015] The alkali metal and/or the alkaline earth metal contained in the catalyst layer as an NO_x-adsorbing component has no particular restriction as to the kind. There can be mentioned, for example, as alkali metals, Li, Na, K and Cs and, as alkaline earth metals, Ca, Ba and Sr. When of these, an alkali metal having high reactivity with Si, particularly K is used as an NO_x-adsorbing component, the effect of the present invention is largest.

25 [0016] The catalyst layer may contain, in addition to the NO_x-adsorbing component such as alkali metal or alkaline earth metal, a noble metal such as Pt, Pd, Rh or the like. These noble metals allow the NO and O₂ present in exhaust gas to react with each other prior to the adsorption of NO_x by alkali metal or alkaline earth metal, and generate NO₂, or, when the once-adsorbed NO_x is released, allow the NO_x to react with combustible components in exhaust gas and make them harmless. The material composing the catalyst layer is preferably a heat-resistant inorganic oxide having a large specific surface area, such as γ -Al₂O₃ so that an NO_x-adsorbing component and a noble metal both mentioned above can be loaded thereon in a highly dispersed state.

45 [0017] The present invention is described in more detail below by way of Examples. However, the present invention is in no way restricted to the Examples.

50 [Preparation of slurries for washcoating for formation of NO_x-adsorbing catalyst layer]

55 [0018] A commercial γ -Al₂O₃ powder having a specific surface area of 200 m²/g was immersed in a solution obtained by mixing an aqueous (NH₃)₂Pt(NO₂)₂ solution and an aqueous KNO₃ solution. The resulting material was stirred in a pot mill for 2 hours and then sub-

7L-46

jected to evaporation to dryness to remove the water. The water-removed material was subjected to dry disintegration and then fired in an electric furnace at 600°C for 3 hours. To the thus-obtained (Pt+K)-predoped γ - Al_2O_3 powder were added an Al_2O_3 sol and water. The resulting mixture was subjected to wet grinding in a pot mill to prepare a slurry for wash coating. The quantitative relation of γ - Al_2O_3 , Pt and K was adjusted at the stage of the above mixing and immersion so that when the slurry was washcoated on a honeycomb carrier and the coated honeycomb carrier was fired, the amount of catalyst layer loaded was 100 g per liter of honeycomb carrier, the amount of Pt was 30 g per cft of honeycomb carrier (1.06 g per liter), and the amount of K was 20 g per liter of honeycomb carrier. The Al_2O_3 sol was added in such an amount that its solid content became 5% by weight of the total Al_2O_3 ; and the water was added in such an amount that the slurry obtained had a viscosity appropriate for wash coating.

[Preparation of samples]

[0019] First, there were prepared 6 kinds of aluminum titanate honeycomb carriers containing Si in an amount of 0% by weight, 0.2% by weight, 1.5% by weight, 3.0% by weight, 5.5% by weight or 12.0% by weight [each honeycomb carrier had a partition wall thickness of 6 mil (0.15 mm), a cell density of 400 cpsi (62 cells/cm²) and a tetragonal cell shape]. A step of washcoating the above-prepared slurry on each honeycomb carrier and drying the coated honeycomb carrier was repeated until the amount of the catalyst layer loaded became 100 g per liter of honeycomb carrier. Then, each resulting honeycomb carrier was fired in an electric furnace at 600°C for 1 hour to obtain NO_x -adsorbing catalysts 1 to 6.

[Durability test]

[0020] Each of the NO_x -adsorbing catalysts 1 to 6 was subjected to an accelerated durability test in an electric furnace at 850°C for 50 hours in the presence of 10% of water.

[Evaluation]

[0021] Each of the NO_x -adsorbing catalysts 1 to 6 was measured for initial bending strength, bending strength after durability test, initial thermal expansion coefficient and thermal expansion coefficient after durability test. The results are shown in Table 1.

Table 1

	Si content in carrier (wt. % as oxide)	Bending strength (kgf/mm ²)		Thermal expansion coefficient ($\times 10^{-6}/^\circ\text{C}$)	
		Initial	After durability test	Initial	After durability test
NO_x -adsorbing catalyst 1 (Comparative Example)	0	0.34	0.15	0.41	1.37
NO_x -adsorbing catalyst 2 (Comparative Example)	0.2	0.38	0.20	0.46	1.43
NO_x -adsorbing catalyst 3 (Example)	1.5	0.74	0.48	0.51	1.79
NO_x -adsorbing catalyst 4 (Example)	3.0	0.83	0.52	0.53	1.85
NO_x -adsorbing catalyst 5 (Example)	5.5	0.97	0.66	0.72	2.01
NO_x -adsorbing catalyst 6 (Comparative Example)	12.0	0.96	0.64	2.13	4.06

[0022] As shown in Table 1, the NO_x-adsorbing catalysts 3 to 5 according to the present invention gave good results in both bending strength and thermal expansion coefficient. Similar results were obtained also when the cell structure of the aluminum titanate honeycomb carrier was changed to a partition wall thickness of 4 mil (0.10 mm) and a cell density of 400 cpsi (62 cells/cm²), or 3 mil (0.075 mm) and 600 cpsi (93 cells/cm²), or 2 mil (0.05 mm) and 900 cpsi (139.5 cells/cm²) or when the cell shape was changed to a hexagon.

[0023] As described above, in the catalyst for purification of exhaust gas according to the present invention, Si (which has high reactivity with the alkali metal or alkaline earth metal used in the catalyst layer as an NO_x-adsorbing component) is present in a given amount in the carrier-composing material; therefore, when the catalyst is exposed to high temperatures, the alkali metal or alkaline earth metal in the catalyst layer reacts preferentially with the Si and the reaction of the metal with the carrier-composing major component is suppressed. As a result, the deterioration of the carrier by the alkali metal or alkaline earth metal is suppressed and the catalyst can be used over a long period of time. Further, the presence of a given amount of Si in the carrier-composing material allows the carrier to have a higher initial strength and, resultantly, the carrier can have a strength necessary for catalyst carrier even after the carrier has been exposed to high temperatures together with the alkali metal-containing catalyst layer and its strength has decreased slightly.

Claims

1. A catalyst for purification of exhaust gas comprising:
 a carrier, and
 a catalyst layer containing an alkali metal and/or an alkaline earth metal, the catalyst layer being loaded on the carrier,
 in which catalyst the carrier-composing material contains Si in an amount of 0.5 to 10.0% by weight as expressed as an oxide.
2. A catalyst for purification of exhaust gas according to Claim 1, wherein the carrier-composing material contains Si in an amount of 1.0 to 6.0% by weight as expressed as an oxide.
3. A catalyst for purification of exhaust gas according to Claim 1, wherein the carrier has a thermal expansion coefficient of $6.0 \times 10^{-6}/^{\circ}\text{C}$ or less.
4. A catalyst for purification of exhaust gas according to Claim 1, wherein the carrier-composing material is aluminum titanate.

5. A catalyst for purification of exhaust gas according to Claim 4, wherein the carrier-composing material further contains Mg and/or Fe.
6. A catalyst for purification of exhaust gas according to Claim 1, wherein the catalyst layer contains K.
7. A catalyst for purification of exhaust gas according to Claim 1, wherein the carrier is a honeycomb carrier.
8. A catalyst for purification of exhaust gas according to Claim 1, wherein the catalyst layer contains at least one kind of noble metal selected from Pt, Pd and Rh.
9. An exhaust purification system for an internal combustion engine having a catalyst according to any one of claims 1 to 8.
10. An internal combustion engine having an exhaust purification system according to claim 9.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 4065

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
E	EP 1 112 774 A (NGK INSULATORS LTD) 4 July 2001 (2001-07-04) * page 2, paragraph 3 * * page 3, paragraph 10 * * page 4, paragraph 21 - page 5, paragraph 28; claims; examples 17-22, 26, 28, 32; tables 1, 2 *	1-10	B01D53/94 B01J21/06 B01J23/02 B01J23/58
X	EP 0 982 066 A (DEGUSSA) 1 March 2000 (2000-03-01) * page 3, paragraph 20; claims *	1-4, 6-10	
Y		5	
Y	PATENT ABSTRACTS OF JAPAN vol. 006, no. 239 (C-137), 26 November 1982 (1982-11-26) & JP 57 140645 A (MATSUSHITA DENKI SANGYO KK), 31 August 1982 (1982-08-31) * abstract *	5	
A	EP 0 787 522 A (TOYOTA MOTOR CO LTD) 6 August 1997 (1997-08-06) * page 3, line 11 - line 15 * * page 6, line 51 - page 7, line 1; claims; tables 1-8 *	1-10	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B01D B01J
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 10 August 2001	Examiner Eijkenboom, A
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EP 01 30 4065 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 4065

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-08-2001

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1112774	A	04-07-2001	NONE	
EP 0982066	A	01-03-2000	DE 19838282 A	02-03-2000
			AU 4466799 A	09-03-2000
			BR 9903875 A	31-10-2000
			CN 1263789 A	23-08-2000
			JP 2000084405 A	28-03-2000
			PL 335071 A	28-02-2000
			TR 9902000 A	21-04-2000
JP 57140645	A	31-08-1982	JP 1483897 C	27-02-1989
			JP 63034781 B	12-07-1988
EP 0787522	A	06-08-1997	JP 9206595 A	12-08-1997
			AU 690481 B	23-04-1998
			AU 1247797 A	28-08-1997
			KR 210538 B	15-07-1999
			US 6251820 B	26-06-2001

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82